

# Mars<sup>™</sup> ClimaPlus<sup>™</sup>





Mars Panels with CLIMAPLUS Superior Performance/ Donn DX® Suspension System

#### **ESD** Information

Recycled Content: 76%

CLIMAPLIS Superior Performance for Mould/Mildew

IEQ						Ene	Mat
Increase Daylight Levels	Lighting	Internal Noise Level Reduction	Low Volatile Organic Compounds	Low Formaldehyde	Mould Prevention	Lighting Density Reduction	Design for Disassembly
+	+	+	1	1	1	+	./

#### Advantages

- Fine, monolithic texture.
- High light reflectance (LR .89).
- Excellent noise reduction (NRC .70).
- Durable, scratch-resistant, cleanable surface.
- Low maintenance panels look like new for years to come.
- CLIMAPLUS 30-year lifetime system warranty to withstand conditions up to 40°C/95% relative humidity without visible sag when used with a Donn® Brand suspension system.


### **Applications**

- Open-plan offices
- Corridors
- Department stores
- Offices with indirect lighting
- Reception areas and lobbies
- Restaurants


#### Substrate

- X-Technology mineral fibre

### **Grid Options**









Information

usgboral.com info.au@usgboral.com info.nz@usgboral.com

**ESD Information** greenusg.com.au greenusg.co.nz

<u>~</u>	Edge	Panel Size <sup>1,2</sup>	Class	Item No	NRC <sup>3</sup>	CAC <sup>3</sup>	LR4	Colour	Grid Options	VOC Emissions	Recycled Content
Year System Warranty No visible sag Mould/mildew protection			0		٥		0		•	3	<b>(∆)</b> (⊪c)
Mars CLIMAPLUS Panels	SQ	600 x 600 x 19mm	Class A	ME86185	.70	35-39	.89	White	A, C	Low	76%
		1200 x 600 x 19mm	Class A	ME88185	.70	35-39	.89	White	A, C	Low	76%
	SLT	600 x 600 x 19mm	Class A	ME86785	.70	35-39	.89	White	В	Low	76%
		1200 x 600 x 19mm	Class A	ME88785	.70	35-39	.89	White	В	Low	76%
	FLB	600 x 600 x 19mm	Class A	ME86985	.70	35-39	.89	White	D	Low	76%
		1200 x 600 x 19mm	Class A	ME88985	.70	35-39	.89	White	D	Low	76%
7	Legend		1	φ:	SAC 0.85	+ all option	ıs (500-40	000 Hz speed	ch range)		
	Low emitting p Services Stand CHPS database	Emissions (VOC Class) performance meets CA Specification 013 dard Practice for the testing of VOC emisse for low-emitting materials. USG Certific s) is available on request. Low emitting is	sions) and is listed ate of Compliance	ealth Lifet d on to w e for Low	time syster rithstand c		to 40°C/95	of 30 years) 5%RH when tems.	Classi recycle panel	composition of post-	
	A	В		С		D					
Grid Profile Options	DX®	DX	\	Centricitee DXT		Centricitee					

#### Physical Data/ Footnotes

### Weight

4.7 kg/m<sup>2</sup>

Environmental Limitations 40°C, 95% RH max.

Thermal Resistance R 0.39 °C/W

Maximum Backloading 0 kg/m<sup>2</sup>

Can be cleaned easily with a soft brush or vacuum

#### Installation

Shall not begin until the building is fully enclosed, watertight, dry, permanent heating and cooling equipment is in operation, residual moisture from wet trades (eg. terrazzo, concrete, plaster) has dissipated, and is free of chemical fumes. Do not mix production lots in the same ceiling area.

#### Scrubbability

Exceeds 1000+ scrub cycles without surface break or the extent of abrasion (ASTM D2486).

Washability Exceeds 1000+ wash cycles without surface break or the extent of abrasion (ATSM D4828).

#### Water resistance

Absorption of 1,660 gm/m<sup>2</sup> per Cobb test (T441 om-84).

## Proprietary technology This product's unique combination

of sag resistance and sound performance results from proprietary technology.

#### - Quaternary ammonium - Sodium hypochlorite

Footnotes

1. Not all panel sizes available in

Cleaning Recommendations

To clean panel, use a clean, white

cloth with water or a mild detergent and wipe surface. To disinfect panel, lightly spray surface and wipe clean

with a clean, white cloth. Acceptable colourless disinfectants include:

- all geographic areas Some imperial sizes available to order
- NRC to ASTM C423 CAC to ASTM E1414
- LR values are shown as averages
   Panel face and back surfaces treated with a patented, broadspectrum antimicrobial standard formulation that inhibits and retards the growth of mould/

## Hydrogen peroxide Isopropyl alcohol

Acoustic Test Standards

# **Available from**



Tel: 1300 655 035 www.renhurst.com

#### Reaction to Fire

Standard	Flame Spread	Smoke Developed			
ASTM E84	< 25	< 50			
AS/NZS 3837	Group Number Classification : 1 unsprinklered				
ISO 5660 Parts 1 & 2	Group Number Classific	cation : 1 - S			

Australia: 1800 226 215